

Surface Insensitive SI 200 Cyanoacrylate Adhesive

LIQUID PROPERTIES

Ester Base ethyl-2-

cyanoacrylate

Appearance Clear, colourless

Flashpoint >81°C
Density 1.05
Shelf Life 12 months,

unopened

Viscosity (Brookfield) @ 25°C 200cP

(Spindle 1, 20rpm)

POLYMER PROPERTIES

Appearance Clear, colourless Softening Point c. 130° C Refractive Index, n_D^{20} 1.45 Full Cure Time 24 hours

Solubility DMF, acetonitrile, acetone

CURED PERFORMANCE

Cure Speed

| Balsa / Balsa | <5 seconds |
|-------------------------------|----------------|
| Oak / Oak | 90-180 seconds |
| Nitrile / Nitrile | <5 seconds |
| Neoprene / Neoprene | <5 seconds |
| EPDM / EPDM | <5 seconds |
| Steel / Steel | 10-20 seconds |
| PVC / PVC | 3-10 seconds |
| Polycarbonate / Polycarbonate | 10-40 seconds |
| | |

Shear Strength

Grit Blasted Steel >15 N/mm²
Etched Aluminium >11 N/mm²
Nitrile Rubber >10 N/mm²
Polycarbonate >12 N/mm²

Tensile Strength

Grit Blasted Steel>18 N/mm²Nitrile Rubber>5 N/mm²Neoprene Rubber>5 N/mm²EPDM Rubber>2.5 N/mm²

PRODUCT STORAGE

Adhesive R&D cyanoacrylates should ideally be stored in original sealed containers until used. Containers should be stored between 10°C and 22°C; avoid exposure to strong light and heat sources. Refrigeration prolongs shelf life.

DISCLAIMER

The data contained within this Technical Data Sheet are furnished for information only and are believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the user to determine the products suitability for use. Adhesive R&D and its distributors and agents accept no liability arising out of the use of this information or the products described herein.